




# BMI Grout 4000 psi



## Product Description:

BMI 4000 is a sand cement grout to fill concrete block or door frames.

## Coverage:

One 80 lb. bag of BMI 4000 makes approximately 0.8 cu. Ft. of grout. BMI 4000 is also available in bulk in our silo mixing station. One ton of BMI 4000 makes approximately 19 cu. ft. of grout.

## Mixing:

BMI 4000 contains all ingredients in dry form, only water needs to be added. Mix one bag of BMI 4000 with approximately 2 gallons of clean water to a pourable consistency

## Application:

Mix grout to a pourable consistency for block and a plastic-like consistency for use with trowel in bond beams and door frames.

## Specifications:

Grout 4000 psi

### Proportions:

Portland Cement Type I	ASTM-C150	1 Part
Sand	ASTM-C144	2 1/2 Parts

### Test Results:

		<i>Compressive Strength</i>	
		<u>7 days</u>	<u>28 days</u>
Slump:	10"	4425	5078
		4464	4966
		4363	4804

## Manufacturer:

**BMI Products of Northern Illinois, Inc.**  
28919 West Route 173  
Antioch, IL 60002-9115  
Phone: (847) 395-7110  
Fax: (847) 395-7105  
Local: (888) SILOMIX  
Web Site: [www.bmi-products.com](http://www.bmi-products.com)

*-These are laboratory tests according to ASTM C-476 and are simulating the strength in the wall—when tested in prisms (not cylinders). Field tests from cylinders will be lower due to the fact that no water absorption has taken place.*

